

AXMINSTER

PREMIUM BROADLOOM

SPECIFICATIONS

MONN | AXMINSTER

Pile Yarn	80% Wool 20% Nylon					
Pile Height	7.00 mm					
Yarn Count	R674 Tex/2					
Backing Materials	Polyester, Polypropylene, SBR Latex, Jute					
Width	3,66 & 4,00 mtr					
	METHOD	7 ROW	8 ROW	9 ROW	10 ROW	11 ROW
Pitch per 10 cm	ISO 1763	27.6	27.6	27.6	27.6	27.6
Rows per 10 cm	ISO 1763	27.6	31.5	35.4	39.4	43.3
Tufts per 100 cm ²	ISO 1763	760	870	980	1086	1195
Total Thickness (mm)	ISO 1765	9.5	9.5	9.5	9.5	9.5
Surface Pile mass (g/m ²)	ISO 8543	774	885	995	1106	1180
Total Pile mass (g/m ²)	Calculated	1024	1170	1316	1463	1560
Total Mass (g/m ²)	ISO 8543	1650	1750	1850	2050	2150
Use Class	SANS 1375-2005	Class 3	Class 4	Class 5	Class 5	Class 5
	EN 1307	Class 32	Class 33	Class 33	Class 33	Class 33
Luxury Class	EN 1307	LC4	LC4	LC5	LC5	LC5
Fire Index Class	SANS 10177-P4	Class 2	Class 2	Class 2	Class 2	Class 2
	EN 13501-1	Class Cfl-s1	Class Cfl-s1	Class Cfl-s1	Class Cfl-s1	Class Cfl-s1

NOTE: Normal Textile tolerances apply. We reserve the right to amend specifications without notice with no detrimental effect on performance.